


# PRODUCT DATA SHEET



Fibre-Reinforced smoothing Compound

# UZIN NC 175



Self-smoothing, fibre-reinforced cementitious smoothing compound with Level Plus Effect for thicknesses up to 20 mm

## Areas of application:

Very low-emission, rakable self-smoothing, fibre-reinforced cement floor-smoothing compound for wood substrates with 3 – 20 mm thickness. Suitable for the fabrication of level installation surfaces with good absorbency for floor covering and wood flooring work. Pump-ready, for interior application.

Suitable for:

- ▶ subsequent flooring of textile and resilient floor coverings of all types
- ▶ subsequent installation of wood flooring
- ▶ subsequent installation of ceramics and natural stone floor coverings
- ▶ high wear in residential, commercial and industrial areas, e.g. in hospitals, high-traffic shopping malls, industrial shops, etc.
- ▶ hot water underfloor heating
- ▶ traffic from chair castors according to DIN EN 12 529

Suitable for use on:

- ▶ wood substrates such as floorboards, multi-ply wood, chipboard P4 – P7 (screw-fixed), OSB 2 – OSB 4 tiles (screw-fixed), wood flooring, or other wood substrates with a number of joints conforming to current British Standards
- ▶ other joint-containing or critical substrates, e.g. precast screed
- ▶ all other common screeds and substrates

\* See important notes.

## Product benefits / properties:

The special advantage of the fibre-reinforced smoothing compound UZIN NC 175 is its high percentage of fibre and plastic. On so-called "problematic substrates", UZIN NC 175 fibrous compound provides both optimal bonding on the substrate as well as maximum reliability with renovation and restoration. UZIN NC 175 completely dries very fast and achieves early readiness for covering even with less favourable climatic conditions.

Provides the highest possible level of emission safety and contributes towards creating a healthy room climate. Marked with the "Blue Angel" for low-emission floor covering adhesives and other installation materials according to RAL-UZ 113.



<b>CE</b>	
0761	
Uzin Utz AG Dieselstraße 3 89079 Ulm	
18	
01/01/0019.01	
EN 13 813:2002	
Fibre-reinforced cementitious levelling compound for interior floor areas	
EN 13 813: CT-C40-F10	
Fire resistance	A2fl-s1
Release of corrosive substances	CT
Compressive strength class	C40
Flexural strength class	F10

UZIN ÖKOLINE



www.blauer-engel.de/uz113  
- No solvents  
- No isocyanates  
- No heavy metals  
- No formaldehyde

[www.blauer-engel.de/uz113](http://www.blauer-engel.de/uz113)



**Composition:** Special cements, mineral aggregates, redispersible polymers, high-performance liquefier, fibres and additives.

- ▶ Superior flow characteristics
- ▶ Rakable (notch size R3)
- ▶ Highly absorbent
- ▶ For layers over 3 mm thick
- ▶ GISCODE ZP 1/Low chromate content according to EU regulation 1907/2006 (REACH)
- ▶ EMICODE EC 1 PLUS/Very low-emission
- ▶ RAL UZ 113/low-emission and hence environmentally compatible

## Technical data:

Packaging:	Paper bag
Pack size:	25 kg
Shelf life:	min. 9 months
Required water quantity:	6 – 6.5 litres per 25 kg bag
Colour:	grey
Consumption:	approx. 5 m <sup>2</sup> at 3 mm per bag
Minimum working temperature:	10 °C at ground level
Ideal working temperature:	20 °C at ground level
Pot life:	25 – 35 minutes*
Ready for foot traffic:	approx. 2 – 3 hours*
Ready for covering:	after approx. 6 hours*
Fire class:	A2fl-s1 acc. to DIN EN 13501-1

\* At 20 °C and 65 % relative humidity at max. 3 mm thickness. See also "Readiness for covering".

UZIN | A brand of Uzin Utz Group

DE | Uzin Utz AG | Dieselstraße 3 | 89079 Ulm | Telefon +49 731 4097-0 | Telefax +49 731 4097-110 | E-Mail [info@uzin.de](mailto:info@uzin.de) | Internet [www.uzin.de](http://www.uzin.de)  
GB | Uzin Utz UK Ltd. | Unit 2, Mitchell Court | Central Park, Rugby, Warwickshire | CV23 0UY | Phone +44 1788 530 080 | Fax +44 1788 536 508  
E-mail [uzin.uk@uzin-utz.com](mailto:uzin.uk@uzin-utz.com) | Internet [www.uzin.co.uk](http://www.uzin.co.uk)

## Subfloor preparation:

The substrate must be sound, load-bearing, dry, free from cracks, clean and free from materials (dirt, oil, grease), that would impair adhesion. Test the substrate in accordance with applicable standards and bulletins and report any deficiencies.

Any adhesion-reducing or unstable layers, e.g. release agents, residues of loose adhesives, smoothing compounds, covering or paint, etc. must be removed, e.g. by brushing off, abrading, grinding or by intensive sanding, for example, with Wolff Mambo with Ninja grinding disc. Intensively sand floorboards, chipboard and all other wooden substrates; retighten screws, if necessary. Thoroughly vacuum loose material and dust.

Use a suitable primer from the UZIN product range according to the type and condition of the substrate. Allow any primers that are applied to dry completely.

Refer to the product data sheets for the products used.

## Application:

1. Pour 6 – 6.5 litres of cold, clean water into a clean container. Add bag contents (25 kg) into the water whilst stirring vigorously until a creamy and lump-free compound is obtained. Use agitator with the UZIN levelling compound stirrer.
2. Pour compound onto the substrate and spread uniformly with the smoothing trowel or rake (notch size R3). With thicker layers the already excellent flow characteristics and the surface can be improved even further by using the UZIN spike roller. Spread the UZIN NC 175 preferably in one application at the desired thickness.

## Consumption information:

Thickness	Approx. coverage per 25 kg bag
3 mm	5.2 m <sup>2</sup>
5 mm	3.1 m <sup>2</sup>
10 mm	1.5 m <sup>2</sup>

## Ready for covering:

Top covering provided	Ready for covering at 20 °C / 65 % rel. humidity	
Textiles and resilient flooring (e.g. PVC, linoleum, rubber), ceramic and natural stone flooring	3 mm	approx. 6 hours
	5 mm	approx. 6 hours
	10 mm	approx. 24 hours
	20 mm	approx. 48 hours
Textiles and resilient floor coverings with Sigan 1 or Sigan Elements Plus + Planus primer	3 mm	approx. 12 hours
Wood flooring	3 mm	approx. 15 hours
	5 mm	approx. 15 hours
	10 mm	approx. 24 hours
	20 mm	approx. 72 hours

## Important notes:

- ▶ Shelf life at least 9 months in original packaging when stored in dry conditions. Setting and drying properties may become prolonged with increasing storage period. The properties of the cured material are not affected hereby. Carefully and tightly re-seal opened packaging and use the contents as quickly as possible.
- ▶ Optimum processing at 15 – 25 °C and relative humidity below 65 %. Low temperatures, high humidity, high thickness, non-absorbent or blocked substrates will delay setting, drying and readiness for covering. High temperatures, low humidity and absorbent substrates accelerate setting, drying and readiness for covering. Furthermore, drying progress depends largely on the air changes per hour. Removing moist air, e.g. through brief intermittent full ventilation, is therefore essential to achieving quick readiness for covering.
- ▶ Store in cool and dry conditions in summer and use cold water. Note shortened pot life at high material or ambient temperatures.
- ▶ Expansion, movement and perimeter joints in the substrate must be adopted. Fit UZIN Foam Expansion Strips to any adjoining rising structures to prevent ingress of the compound into the connection joints. Expansion strips are generally necessary for thicknesses over 5 mm. On wooden substrates the expansion strip must be completely removed after levelling work.
- ▶ The substructure of wooden floors must be dry to prevent damage due to damp through rotting or mould formation. Adequate ventilation or rear-ventilation must be provided especially when installing impermeable flooring, e.g. by removing the existing expansion strip or by installing special skirting with vent openings. NC 175 will not disguise the deformation of any wooden substrate if any climatic conditions change and the substrate moves.



- ▶ Can be pumped with continuously mixing spiral pumps, e.g. from manufacturers such as m-tec, P.F.T. and others.
- ▶ Rooms without a basement underneath must be sealed against rising dampness in compliance with standards.
- ▶ Min. thickness 3 mm. Rakable with notch size R3.
- ▶ When smoothing in several layers allow the compound to dry completely, prime in between with UZIN PE 360 and apply, for example, UZIN NC 170 LevelStar fine or follow-up smoothing compound after drying (1 hour\*). The thickness of the second smoothed layer must not exceed the thickness of the first one.
- ▶ For thicknesses above 10 mm or on moisture-sensitive (calcium sulphate screeds) or weak substrates (adhesive residues), use reaction epoxy resin primers, such as UZIN PE 460/PE 480 or UZIN PE 404, gritted.
- ▶ Use UZIN PE 630 for priming on floorboards and other substrates with joints. On weak, creaking or slightly cushioned substrates the "resilient" primer UZIN KR 410 needs to be rolled on and gritted. Where thicknesses exceed 10 mm, an epoxy resin primer such as UZIN PE 460, gritted, is required.
- ▶ To prevent damage due to damp for wooden floors, they must be permanently dry. The wood moisture shall correspond to the room climate.  
Adequate ventilation must be provided especially when installing impermeable coverings, e.g. by integrating ventilation slots. Floorboards must not move against each other and need to be completely fastened on the supporting beams (e.g. by screw-fixing).
- ▶ On weak older substrates with several layers of adhesive or levelling compound the use of the fibre-reinforced gypsum-based levelling compound UZIN NC 115 is to be preferred.
- ▶ Can be used on mastic asphalt (screed) if resilient or textile floor coverings shall subsequently be installed and the mastic asphalt corresponds to the hardness classes IC 10 and IC 15 acc. to DIN EN 13 813
- ▶ For new mastic asphalt screeds thicknesses up to max. 5 mm, and for older mastic asphalt screeds with old layers attached, thicknesses up to max. 3 mm are permissible. For greater thicknesses gypsum-based smoothing compounds such as UZIN NC 110 or UZIN NC 115 are to be used.
- ▶ Do not use in exterior or wet areas.
- ▶ Protect freshly smoothed areas from draughts, direct sunlight and sources of heat. Cementitious compound layers on soft or tacky substrates tend to stress crack propagation. These soft or tacky layers must therefore be removed before applying smoothing compounds. Leaving such compound layers open too long also promotes cracking and should therefore be avoided.
- ▶ Do not use as wearing floor covering or wearing surface; always apply a top covering.
- ▶ Smoothing compound must not enter between insulation and heating pipes because of the risk of corrosion. This applies in particular for heating pipes from galvanized steel. Insulation may only be cut off after smoothing.

- ▶ Follow the generally acknowledged rules of the trade and practice for the installation of wood flooring and floor covering of the respective applicable standards (e.g. EN, DIN, Ö-standard, SIA, etc.).
- ▶ The following standards and bulletins represent supporting information and are recommended for special attention:
  - DIN 18 365 "Working with floor covering", Ö-Norm B 2236
  - DIN 18 356 "Working with wood flooring", Ö-Norm B 2218
  - DIN 18 352 "Tile and slab work"
  - TKB publication "Assessment and preparation of substrates for floor covering and wood flooring installation"
  - BEB bulletin "Assessment and preparation of substrates"
  - TKB publication "Technical description and application of cementitious floor smoothing compounds"
  - ZVPF bulletin "Quality requirements on the flatness of substrates for floor covering and wood flooring"

### Health and safety, environmental protection:

Contains cement, low-chromate content as per directive EU-VO 1907/2006 (REACH) – GISCODE ZP 1. Store out of reach from children! Wear nitrile-soaked cotton gloves. Wear protective dust mask when mixing. Provide thorough ventilation during and after application/drying! Do not eat, drink or smoke while working with the product. In the event of contact with the eyes or skin, rinse immediately with plenty of water. Do not dispose of into the sewer system, open water or the soil. Clean tools with water and soap immediately after use.

Physiologically and ecologically harmless when cured and dry.

The basic prerequisites for optimal room air quality after floor covering work consist of installation conditions conforming to standards and well-dried substrates, primers and levelling compounds.

Information for persons with allergies available at +49 (731) 4097-0 (Germany).  
EMICODE EC 1 PLUS – Very low-emission.

### Disposal:

Collect and reuse product residues wherever possible. Do not dispose of into the sewer system, open water or the soil. Paper sacks emptied from any residues can be recycled. Collect product residues, mix with water, allow to harden and dispose of as construction waste.

