


## custom hospitality carpets



CREATIVE DESIGN, FLAWLESS EXECUTION

# CARPET INSTALLATION GUIDE



### Installation of DESSO® carpet

A carpet's life will be governed by many factors, starting with the selection process that must take both aesthetic and performance considerations into account. However, the installation process is of critical importance for an optimal performance of carpet.

The following installation procedures are guidance for a proper installation of Desso carpet, and should be followed at all times.

### Preparations

### Site conditions

The following conditions inside the building are critical for proper installation:

- 1. The temperature of the floor must be between 59°F/ 15°C and 65°F/ 20°C. The temperature of the room must be 59°F/ 15°C at minimum.
- 2. With the standard CM-measurement, the damp content of a concrete slab should never exceed 3%. Using the alternative protimeter measurement method, the damp content should not exceed 5%. The humidity in the room should stay below 60%.
- 3. The alkalinity or pH in a concrete slab should be between 5 and 9 for a direct-glue installation. Should pH be outside this range, stop and do not proceed with the installation. Remedial action will be necessary.
- 4. Newly poured concrete floors generally take 90-120 days to cure. Please take into account that a concrete subfloor must be dry, clean, flat, solid and free from grease. A suspended cement-bonded subfloor demands a good isolation layer as well. Gypcrete or substrates with excessive dust must be cleaned, and then primed with a latex primer.
- 5. In cold and damp seasons the carpet must be allowed to acclimatize for at least 24 hours in the surroundings in which it is to be laid, before the fitting is commenced.
- 6. For rooms with floor heating systems, the only technique applied is full adhesion. The heating temperature needs to be reduced 24 hours before installing. The heating system can be turned up slowly 48 hours after installation. During wintertime, the floor temperature has to be reduced to a level between 59°F/ 15°C and 65°F/ 18°C.

### Trimming the selvedge edge

In most cases, you will have to trim the selvedge edge on one side or both. If this is the case, make sure you seal the edge properly with a latex seam sealer. When you place both breadths together, you should not exceed 1/8" or 0.3cm with no face yarns, or unsightly seams will ensue.

### Proper tools

- dead man
- power stretcher
- mini-stretcher
- stay nails
- dry lines (masonry line)

### General guidelines

Fitting patterned carpet requires a great deal more attention and time than plain carpet. A good section plan that takes correct matching and pattern repeat length into account is an essential component of fitting patterned carpet.

### Pattern shifting (run out)

Slight pattern shifting should always be taken into account. Pattern shifts can not only occur during the production process, but also as a result of shrinkage under changing atmospheric conditions (e.g. during transport). Any pattern shift, however small, will have to be corrected when fitting. The extent to which any pattern shift is visible in practice is greatly dependent on the size of the area, the pattern and the color, and the corrections required when fitting.

### Pattern shift between pieces from the same production

A pattern shift may occur within one production. For a pattern repeat length between  $\ge 0$ "/ 0cm and < 4"/ 10cm, the maximum deviation is 2% of the pattern repeat. For pattern repeat length between  $\ge 4$ "/ 10cm and < 40"/ 100cm, the maximum deviation is 1% of the pattern repeat. For the maximum deviation for any pattern repeat length above 40"/ 100cm, please contact your local sales representative.

### Bowing

Z-bowing is defined as the deviation from squareness. The edges of the strip sections do not lie in one line. In this case a maximum deviation of 1.2"/ 3cm over a 400cm/ 13' 1.5" width is permitted. S-bowing is defined as the bowing in relation to a straight line on the strip section. A maximum deviation of 1.2"/ 3cm over a 400cm/ 13' 1.5" width is also applicable in this case.

### Stretch-in

Stretching with the carpet gripper method is the oldest used installation technique, but grippers have improved a lot. This method has advantages to other fitting techniques, like:

- better walking comfort
- improved thermal and acoustic isolation
- removal and replacement can easily be done
- lifetime of the floor covering can be enhanced by using an underlay
- certain preparations for leveling the subfloor can usually be omitted


However, the stretching technique is more time consuming than gluing, due to the preparation required.

The first step is to dry-lay the area to be carpeted. When using multiple breadths, install the largest pattern first using control lines to keep the patterns square to the area. Install the first breadth, and then install the second. Make the seam and continue in this fashion.

Place a piece of carpet between the tailpiece and wall to prevent damage to the wall. Stretch the carpet following the examples and sequences provided below.

The wall to which the carpet is attached before stretching, has to be chosen in function of the highest tension to be used lengthwise. Begin stretching the carpet from a corner and secure. Now use the power stretcher to stretch the carpet fully. Position the tailpiece in the corner in which you started and stretch the carpet towards the opposite corner.

Use strong profiled edging trims on areas where the carpet ends and a different floor surface begins. A profiled edging trim will help prevent damage and unraveled edges.



### Stretch-in using seam tape

We recommend on stretch-in to use a low profile seam tape. As you are making the seam, use a flat roller to make sure the thermo-plastic from the seam tape is penetrating the back of the carpet to make a stable seam. Use a latex seam seal to seal the edges of the seam after trimming the selvedge edge.

### Stretch-in using a star-tractor

When using a star-tractor, ensure that the heat from the iron and tractor are set to the correct temperature to avoid re-crimp of the yarns. The use of a star-tractor is not recommended by Desso.



### Direct glue

After the carpet has been dry laid and acclimated, use control lines every other pattern. Using a knee-kicker, align the patterns as close as possible to the control line. This allows you to visually know how you will need to move the carpet prior to spreading any adhesive.

Open up half the first breadth and half the second breadth. Glue the area by using a 1/8" x 1/8" x 1/8" or 0.3 x 0.3 x 0.3 cm. U-notch trowel. Lay the breadths back in. Setup control lines and by using a power stretcher and/or mini stretcher, align the patterns to the control lines. You may have to use stay nails to hold in place until the adhesive sets up.

### Seams

Seams should be sealed on the direct glue down using a solvent-base sealer. Apply a 1/8 bead of seam sealer to the base of the edge at the first seam. Roll the second seam into the first. This will seal both edges to keep from fraying or unraveling.

### Double stick

Before commencing the installation, always read the instructions supplied with the adhesive with respect to site conditions (temperature and humidity), the type of adhesive spreader required, the correct type of adhesive and the quantity to be used.

### Installing carpet

After the carpet has been dry laid and acclimated, use control lines every other pattern. Using a knee-kicker, align the patterns as close as possible to the control line. This allows you to visually know how you will need to move the carpet prior to spreading any adhesive.

Open up half the first breadth and half the second breadth. Glue the area. Lay the breadths back in. Setup control lines by using a power stretcher and/or mini stretcher and align the patterns to the control lines. You may have to use stay nails to hold in place until the adhesive sets up.

Carpet needs to be rolled with a roller, maximum weight 35 lbs or 16kg. There should be no heavy foot or rolling traffic on the carpet for a minimum of 24 hours.



#### Double-stick seams

It is required to use double stick seam tape to ensure seam stability.

### Installing stairs

The carpet should be installed so the pile direction is in the down-the-stair direction. This ensures the carpet will wear better because foot traffic is the same as pile direction. Never position seams across stair nosings unless installing protective nosings such as plastic or aluminum strips.

### Woven-to-plan panels

Many times referred to as Electronic Jacquard or E.J., the technology of woven-to-plan panels has changed the way borders, inserts and out fields are all woven together to fit the space. Qualified installers are able to take 2 rolls of carpet and seam them together with one seam as opposed to seaming together the insert, border, outfield and end caps like a puzzle.

The installation package includes:

- Rolls labeled
- Control sheet
- Seaming diagrams
- Production diagram of each roll
- Flooded prints

### Installation

Dry-lay all panels to ensure they line up. Be sure to check columns, light fixtures, soffits, and wall dividers while you are dry laying the carpet to make sure these areas are aligned. This will give you the opportunity to make adjustments prior to spreading any adhesive.

Do not glue any carpet if it does not match. If you have something that doesn't match, stop the installation and call Desso's Service Support immediately.

### After installation: carpet protection

During construction works, carpet should be protected from heavy traffic and construction dust with a non-staining building material paper such as kraft paper or protective cardboard or special carpet sheeting like Easydek.

It is essential that the adhesive on the carpet is dry before protection is applied. Ensure that a minimum of 24 hours – but preferably 48 hours – drying time is taken into account and always follow the instructions provided by the manufacturer of the glue. Placing protective sheeting on the carpet before the adhesive is dry can cause capture of moisture, with pile reversal and irreparable damage as a consequence.

### Notes

- When using adhesive, never cut carpet that already has adhesive applied to the back. When trimmings are removed, adhesive will be removed as well from critical locations.
- When installing carpet using any of the methods described above, ensure that the pile is standing up straight and that no piles are pinched into the seam.

### Contact information **Headquarters**

#### **Headquarters Desso**

Taxandriaweg 15 5142 PA Waalwiik The Netherlands

#### Showrooms Belgium

Robert Ramlotstraat 89 9200 Dendermonde

#### France

Parc du pont de Flandre 11 Rue de Cambrai F-75 019 Paris France

#### Middle East

Sultan Ali Al - Owais Building SATWA PO Box 24310 Dubai

T: +31 (0)416 684 100 F: +31 (0)416 335 955 www.desso.com

T: +32 522 62 480 F: +32 522 62 489 service-be@desso.com

T: +33 155 26 39 39 F: +33 155 26 39 40 service-fr@desso.com

T: +971 439 859 00 F: +971 439 859 08 service-mea@desso.com

#### Netherlands

Taxandriaweg 15 5142 PA Waalwijk The Netherlands

#### Poland

Plac Piłsudskiego 2 00-073 Warszawa

#### Russia

Pokrovka Street 33/22 Office 418 Moscow 105062

#### Spain

Torre de Valencia C/O'donnell, 4 - 1ra. Planta - Of. 19 - 20 F: +34 914314678 28009 Madrid

#### United Kinadom

23-25 Great Sutton Street London EC1V 0DN United Kingdom

T: +31 (0)416 684 100 F: +31 (0)416 335 955 info@desso.com

T: +48 22 331 32 22 F: +48 22 331 32 23 service-pl@desso.com

T: +7 495 225 9408 F: +7 495 225 9409 service-ru@desso.com

T: +34 914361805 service-es@desso.com

T: +44 20 7324 5500 F: +44 20 7324 5510 service-uk@desso.com

### Sales offices and dealers

(for complete addresses of our global sales offices, please visit www.desso.com)

Albania, Croatia & Balkens T: +385 1615 55 50 service-hr@desso.com

Asia T: +31 416 684 229 service-asia@desso.com

Argentina T: +54 (911) 6908 0081 service-latam@desso.com

Austria T: +43 1 716 44-0 office@ambiente-textil.at

Australia T: +617 3881 1777 sales@gibbongroup.com.au

**Belgium & Luxemburg** T: +32 522 62 480 service-be@desso.com

Brazil T: +55 11 9600 3864 service-br@desso.com

Bulgaria T: +48 660 490 160 service-bg@desso.com

Central America/Andean/ Carribean T: +57 1 618 0537 service-latam@desso.com China (Southern) M: +86 13 801 884 918 service-china@desso.com

China (Northern) M: +86 13 501 064 621 service-china@desso.com

Colombia T: +57 (0)1618 0537 service-co@desso.com

Czech Republic T: +42 0774 993 723 service-cz@desso.com

Denmark T: +45 383 231 55 service-dk@desso.com

Finland T: +358(0) 10 6665 170 service-fi@desso.com

France T: +33 155 26 39 39 service-fr@desso.com

Germany T: +49 6122 58 73 410 service-de@desso.com

Hungary T: +36 1 250 1420 service-hu@desso.com Italv T: +80 007 650 765 service-it@desso.com

Japan T: +81-3-3274-3303 service-japan@desso.com

Mexico T: +52 1(55) 5540 7616 service-me@desso.com

Middle East T: +971 439 859 00 service-mea@desso.com

Norway T: +47 241 597 16 service-no@desso.com

Poland T: +48 22 331 32 22 service-pl@desso.com

Portugal T: +35 1 229 828 110 service-pt@desso.com

Romania T: +48 660 490 160 service-ro@desso.com

**Russia/Baltics** T: +7 495 225 9408 service-ru@desso.com Slovakia T: +42 0774 993 723 service-sk@desso.com

South Africa T: +31 416 684 125 info@desso.co.za

Spain T: +34 91436 1805 service-es@desso.com

Sweden/Finland T: +46 853 188 052 support@ardbogolv.se

Switzerland T: +41 55 645 21 11 service-ch@Desso.com

The Netherlands T: +31 416 684 130 service-nl@desso.com

Turkey T: +90 212 287 61 58 service-tr@desso.com

**United Kingdom** T: +44 1235 554 848 service-uk@desso.com

USA T: +1 203 202 7650 service-us@desso.com



