Tide

Preliminary specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1	/10 "						
Aspect	ISO 2424	Structured loop pile (pattern repeat: L 54cm / W 18cm)								
Dye method		Solution dyed								
Width		cm	400		ft	13.1				
Primary backing	ISO 2424		Polyester - polyamide fleece							
Secondary backing	ISO 2424		Polypropylene woven - Sandwich Backing							
Pile fibre composition	ISO 2424		BCF Polyamide 6 ECONYL [®] (ECONYL [®] is made from 100% regenerated content) **							
Total thickness	ISO 1765	mm	8.0		inch	0.3				
Effective pile thickness	ISO 1766	mm	4.8		inch	0.19				
Total mass	ISO 8543	g/m²	2250		oz/yd²	66.4				
Total pile mass	ISO 2424	g/m²	710		oz/yd²	21.0				
Effective pile mass	ISO 8543	g/m²	440		oz/yd²	13.0				
Pile density	ISO 8543	g/cm³	0.092		lb/in ³	0.0033				
Number of tufts	ISO 1763	/dm²	1580		/yd²	132104				
Stroll test	ISO 6356	kV	≤ 2,0							
Vertical resistance	ISO 10965	Ohm								
Horizontal resistance	ISO 10965	Ohm								
Use classification	EN 1307		32 Commercial - general use							
Luxury rating	EN 1307		LC 2							
Impact sound reduction ΔL_w	ISO 10140	dB	30							
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000		
		α _s	0.00	0.06	0.13	0.30	0.52	0.51		
Noise reduction	ISO 354	α	0.25							
Thermal resistance	ISO 8302	m².K/W	≤ 0,17							
Flammability	EN 13501-1	EN 13501-1		Cfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.	www.pro-dis.info		BA						





Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognised trade standards. An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorco-verings. Note: Tarkett reserves the right to amend this specification without giving prior notice. For the latest versions of the technical specifications, visit www.desso.com

EN-20180308

